

# Fire Sprinkler Pipe

Schedule 10 and Schedule 40

## Submittal Data Sheet



### FM Approved and Fully Listed Sprinkler Pipe

Wheatland's Schedule 10 and Schedule 40 steel fire sprinkler pipe is FM Approved and UL, C-UL and FM Listed.

### Approvals and Specifications

Both products meet or exceed the following standards:

- ASTM A135, Type E, Grade A (Schedule 10)
- ASTM A795, Type E, Grade A (Schedule 40)
- NFPA 13

### Manufacturing Protocols

Schedule 10 and Schedule 40 are subjected to the toughest possible testing protocols to ensure the highest quality and long-lasting performance.

### Finishes and Coatings

All Wheatland black steel fire sprinkler pipe up to 6" receives a proprietary mill coating to ensure a clean, corrosion-resistant surface that outperforms and outlasts standard lacquer coatings. This coating allows the pipe to be easily painted, without special preparation. Schedule 10 and Schedule 40 can be ordered in black, or with hot-dip galvanizing, to meet FM/UL requirements for dry systems that meet the zinc coating specifications of ASTM A795 or A53. All Wheatland galvanized material is also UL Listed.

### Product Marking

Each length of Wheatland fire sprinkler pipe is continuously stenciled to show the manufacturer, type of pipe, grade, size and length. Barcoding is acceptable as a supplementary identification method.

## SCHEDULE 10 SPECIFICATIONS

NPS	NOM OD		NOM ID		NOMINAL WALL		NOMINAL WEIGHT		UL	PIECES
	in.	mm	in.	mm	in.	mm	lbs./ft.	kg/m		
1¼	1.660	42.2	1.442	36.6	.109	2.77	1.81	2.69	7.3	61
1½	1.900	48.3	1.682	42.7	.109	2.77	2.09	3.11	5.8	61
2	2.375	60.3	2.157	54.8	.109	2.77	2.64	3.93	4.7	37
2½	2.875	73.0	2.635	66.9	.120	3.05	3.53	5.26	3.5	30
3	3.500	88.9	3.260	82.8	.120	3.05	4.34	6.46	2.6	19
4	4.500	114.3	4.260	108.2	.120	3.05	5.62	8.37	1.6	19
5	5.563	141.3	5.295	134.5	.134	3.40	7.78	11.58	1.5	13
6	6.625	168.3	6.357	161.5	.134	3.40	9.30	13.85	1.0	10
8	8.625	219.1	8.249	209.5	.188	4.78	16.96	25.26	2.1	7

\* Calculated using Standard UL CRR formula, UL Fire Protection Directory, Category VIZY.

\* The CRR is a ratio value used to measure the ability of a pipe to withstand corrosion. Threaded Schedule 40 steel pipe is used as the benchmark (value of 1.0).

## SCHEDULE 40 SPECIFICATIONS

NPS	NOM OD		NOM ID		NOMINAL WALL		NOMINAL WEIGHT		UL	PIECES
	in.	mm	in.	mm	in.	mm	lbs./ft.	kg/m		
1	1.315	33.4	1.049	26.6	.133	3.38	1.68	2.50	1.00	70
1¼	1.660	42.2	1.380	35.1	.140	3.56	2.27	3.39	1.00	51
1½	1.900	48.3	1.610	40.9	.145	3.68	2.72	4.05	1.00	44
2	2.375	60.3	2.067	52.5	.154	3.91	3.66	5.45	1.00	30

\* Calculated using Standard UL CRR formula, UL Fire Protection Directory, Category VIZY.

\* The CRR is a ratio value used to measure the ability of a pipe to withstand corrosion. Threaded Schedule 40 steel pipe is used as the benchmark (value of 1.0).



## SUBMITTAL INFORMATION

PROJECT:

---

ENGINEER:

---

LOCATIONS:

---

BLACK

CONTRACTOR:

---

SPECIFICATION REFERENCE:

---

COMMENTS:

---

HOT-DIP GALVANIZED

DATE:

---

SYSTEM TYPE:

---